



# PRODUCT DATA SHEET

## WINFAB 250W

WINFAB 250W is manufactured using high tenacity polypropylene yarns that are woven to form a dimensionally stable network, which allows the yarns to maintain their relative position. WINFAB 250W resists ultraviolet deterioration, rotting and biological degradation and is inert to commonly encountered soil chemicals.

PROPERTY	TEST METHOD	MARV ENGLISH	MARV METRIC
Tensile Strength (Grab)	ASTM D-4632	250 lbs	1110 N
Elongation	ASTM D-4632	15%	15%
Puncture	ASTM D-4833	100 lbs	444 N
Mullen Burst	ASTM D-3786	450 psi	3101 kPa
Trapezoidal Tear	ASTM D-4533	90 lbs	400 N
UV Resistance (at 500 hrs)	ASTM D-4355	70%	70%
Apparent Opening Size (AOS)*	ASTM D-4751	40 US Std. Sieve	0.425 mm
Permittivity	ASTM D-4491	.05 sec <sup>-1</sup>	.05 sec <sup>-1</sup>
Water Flow Rate	ASTM D-4491	4 gpm/ft <sup>2</sup>	163 l/min/m <sup>2</sup>
Roll Sizes		12.5' x 360' 15.0' x 300' 17.5' x 258'	3.81 m x 109.8 m 4.57 m x 91.5 m 5.33 m x 78.6 m

\*Maximum average roll value.

***Willacoochee Industrial Fabrics***  
***Quality at Competitive Prices.***

769 West Main Street  
PO Box 599  
Willacoochee, GA 31650

PH: 912-534-5757  
FAX: 912-534-5533  
[www.winfabusa.com](http://www.winfabusa.com)

Disclaimer: Willacoochee Industrial Fabrics assumes no liability for the completeness or accuracy of this information or the ultimate use of this information. This document should not be construed as engineering advice. Always consult the project engineer for project specific requirements. The end user assumes sole responsibility for the use of this information and product. The property values listed above are subject to change without notice.